



Product Family: [Multilayer Ceramic Capacitors -General Purpose](#)
Part Number Series: [CGL Series](#)

	<p>Construction:</p> <ul style="list-style-type: none"> • High Density, High Efficiency Ceramic Capacitors • NPO, X7R, X5R and Y5V dielectric materials • Wrap around electrodes • 100% matte tin over Ni terminations (RoHS compliant) RoHS 2011/65/EU compliant and Pb Free (100% tin terminations) 	<p>Features:</p> <ul style="list-style-type: none"> • 0201, 0402, 0603,0805, 1206, 1210, and 1812 English sizes (0603 to 4532 Metric) • 0.1pF to 1.0µF capacitance range—high capacitance to size ratio • 4V to 100V • High volume production suitable for commercial and special applications
--	--	---

Description:
 These general purpose chip capacitors are ideal for consumer electronics, telecom, power supply and other applications. They feature a wide range of sizes and a high capacitance for the given component size.

Product Dimensions:

Outline	Size Inch (mm)	L (mm)	W (mm)	T (mm)/Symbol	Soldering Method *	M _B (mm)	
	0201 (0603)	0.6±0.03	0.3±0.03	0.3±0.03	L	R	0.15±0.05
		0.6±0.05 ^{#1}	0.3±0.05 ^{#1}	0.3±0.05 ^{#1}			0.15+0.1/-0.05
		0.6±0.09 ^{#2}	0.3±0.09 ^{#2}	0.3±0.09 ^{#2}			
	0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N	R	0.25 +0.05/-0.10
		1.00±0.20	0.50±0.20	0.50+0.02/-0.05	Q	R	
		1.60±0.10	0.80±0.10	0.5±0.20	E	R	
	0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S	R / W	0.40±0.15
		1.60+0.15/-0.10	0.80+0.15/-0.10	0.50±0.10	H	R / W	
		1.60±0.20	0.80±0.20	0.80+0.15/-0.10	X	R / W	
	0805 (2012)	2.00±0.15	1.25±0.10	0.50±0.10	H	R / W	0.50±0.20
				0.60±0.10	A	R / W	
				0.80±0.10	B	R / W	
		1.25±0.10	D	R			
		2.00±0.20	1.25±0.20	0.85±0.10 ^{#3}	T ^{#3}	R / W	
	1206 (3216)	3.20±0.15	1.60±0.15	0.80±0.10	B	R / W	0.60±0.20 (0.5±0.25) ^{***}
				0.95±0.10	C	R	
		3.20±0.20	1.60±0.20	1.25±0.10	D	R	
		1.15±0.15	J	R			
		1.60±0.20	G	R			
	3.20+0.30/-0.10	1.60+0.30/-0.10	0.85±0.10	T	R / W		
	1210 (3225)	3.20±0.30	2.50±0.20	0.95±0.10	C	R	0.75±0.25
				0.85±0.10	T	R	
				1.25±0.10	D	R	
		3.20±0.40	2.50±0.30	1.60±0.20	G	R	
2.00±0.20		K	R				
1812 (4532)	4.50±0.40 (4.5+0.5/-0.3) ^{**}	3.20±0.30	2.50±0.30	M	R	0.75±0.25 (0.5±0.25) ^{***}	
			1.60±0.20	G	R		
	2.00±0.20	K	R				
	3.20±0.40	2.50±0.30	M	R			
	2.80±0.30	U	R				

* R = Reflow soldering process ; W = Wave soldering process.
 ** For 1808_200V ~3kV, 1812_200V~3kV and safety certificated products.
 *** For 1206_1000V ~3kV,1808_200V ~3kV, 1812_200V~3kV and safety certificated products.
 #1 : For 0201/Cap ≥ 0.68µF products.
 #2 : For 0201/Cap ≥ 1µF products.
 #3 : For 0805/0.22µF/100V/ T thickness:0.85+0.15/-0.1(mm)

Part Numbering: Ex: CGLC0402B101A101J-T10

Series	Termination	English Size (Metric)	Dielectric Type	Rated Voltage	Internal Code	Capacitance Value in pF	Capacitance Tolerance	T&R Packaging Quantity
CGL	C = Cu/Ni/Sn	0201 (0603) 0402 (1005) 0603 (1608) 0805 (2012) 1206 (3216) 1210 (3225) 1812 (4532)	B = X7R F = Y5V N = NPO (COG) X = X5R	3 digits with the first 2 being significant. The last digit specifies the number of zeros. "R" denotes decimal position as necessary. Ex. 6R3=6.3V 101=100V	A	3 digits with the first 2 being significant. The last digit specifies the number of zeros. "R" denotes decimal position as necessary. Ex. 1R5=1.5pF 101=100pF	A = ±0.05pF B = ±0.1pF C = ±0.25pF D = ±0.5pF F = ±1.0% G = ±2.0% J = ±5.0% K = ±10.0% M = ±20.0% Z = -20/+80%	-T05 = 500 -T1 = 1,000 -T2 = 2,000 -T3 = 3,000 -T4 = 4,000 -T5 = 5,000 -T6 = 6,000 -T9 = 9,000 -T10 = 10,000 -T15 = 15,000 -T50 = 50,000 -T70 = 70,000 (see packaging section for offering and corresponding reel diameter)

Electrical Specifications:

Dielectric	NP0	X7R	Y5V	X5R
Size	0201, 0402, 0603, 0805, 1206, 1210, 1812			
Capacitance range*	0.1pF to 0.1µF	100pF to 1µF	0.01µF to 1µF	100pF to 1µF
Capacitance tolerance**	Cap≤5pF ^{#1} : A (±0.05pF), B (±0.1pF), C (±0.25pF) 5pF<Cap<10pF: C (±0.25pF), D (±0.5pF) Cap≥10pF: F (±1%), G (±2%), J (±5%), K (±10%)	J (±5%), K (±10%), M (±20%)	M (±20%), Z (-20/+80%)	K (±10%), M (±20%)
Rated voltage (WVDC)	10V, 16V, 25V, 50V, 100V	6.3V, 10V, 16V, 25V, 50V, 100V		4V, 6.3V, 10V, 16V, 25V, 50V
DF(Tan δ)*	Cap<30pF: Q≥400+20C Cap≥30pF: Q≥1000	Note 1		
Operating temperature	-55 to +125°C		-25 to +85°C	-55 to +85°C
Capacitance characteristic	±30ppm	±15%	+30/-80%	±15%
Termination	Ni/Sn (lead-free termination)			

#1: NP0, 0.1pF product only provide B tolerance; 0603N0R4 provide B&C tolerance; 0603N0R3 only provide C tolerance.

* Measured at the condition of 30~70% related humidity.

NP0: Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2Vrms, 1.0kHz±10% for Cap>1000pF, 25°C at ambient temperature

X7R/X5R: Apply 1.0±0.2Vrms, 1.0kHz±10%, at 25°C ambient temperature.

Y5V: Apply 1.0±0.2Vrms, 1.0kHz±10%, at 20°C ambient temperature.

** Preconditioning for Class II MLCC: Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement.

Note 1:

X5R/X7R

Y5V

Rated Vol.	D.F.≤	Exception of D.F. ≤	
≥100V	≤2.5%	≤3%	1206≥0.47µF
		≤5%	0805>0.1µF; 0603≥0.068µF; 1206>1µF; CLP series
50V	≤2.5%	≤3%	0201(50V); 0603≥0.047µF; 0805≥0.18µF; 1206≥0.47µF
		≤10%	0402≥0.1µF; 0603>0.1µF; 0805≥1µF; CLP series
35V	≤3.5%	≤10%	0603≥1µF
25V	≤3.5%	≤5%	0201≥0.01µF; 0805≥1µF
		≤7%	0603≥0.33µF
		≤10%	0201≥0.1µF; 0402≥0.10µF; 0603≥0.47µF; CLP series
		≤12.5%	0402≥0.47µF
16V	≤3.5%	≤5%	0201≥0.01µF; 0402≥0.033µF; 0603≥0.15µF; 0603≥0.15µF; 0805≥0.68µF
		≤10%	0201≥0.1µF; 0402≥0.22µF; 0603≥0.68µF; CLP series
10V	≤5%	≤10%	0201≥0.012µF; 0402≥0.33µF (0402/X7R≥0.22µF); CLP series
		≤15%	0603≥0.33µF; 01R5 0201≥0.1µF; 0402≥1µF
6.3V	≤10%	≤15%	0201≥0.1µF; 0402≥1µF; CLP series
4V	≤15%	---	---

Rated Vol.	D.F. ≤	Exception of D.F. ≤	
≥50V	≤5%	≤7%	0603≥0.1µF; 0805≥0.47µF
35V	≤7%	---	---
25V	≤5%	≤7%	0402≥0.047µF; 0603≥0.1µF; 0805≥0.33µF; 1206≥1µF
		≤9%	0402≥0.068µF; 0603≥0.47µF
16V (C<1.0µF)	≤7%	≤9%	0402≥0.068µF; 0603≥0.68µF
		≤12.5%	0402≥0.22µF
10V	≤12.5%	≤20%	0402≥0.47µF
6.3V	≤20%	---	---

Capacitance Range—NPO Dielectric (0201, 0402, 0603, 0805 English sizes):

DIELECTRIC		NPO																	
SIZE		0201			0402					0603					0805				
RATED VOLTAGE (VDC)		16	25	50	10	16	25	50	100	10	16	25	50	100	10	16	25	50	100
Capacitance	0.1pF (0R1)	L	L	L	N	N	N	N											
	0.2pF (0R2)	L	L	L	N	N	N	N											
	0.3pF (0R3)	L	L	L	N	N	N	N		S	S	S	S						
	0.4pF (0R4)	L	L	L	N	N	N	N		S	S	S	S						
	0.5pF (0R5)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	0.6pF (0R6)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	0.7pF (0R7)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	0.8pF (0R8)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	0.9pF (0R9)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	1.0pF (1R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	1.2pF (1R2)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	1.5pF (1R5)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	1.8pF (1R8)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	2.0pF (2R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	2.2pF (2R2)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	2.7pF (2R7)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	3.0pF (3R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	3.3pF (3R3)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	3.9pF (3R9)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	4.0pF (4R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	4.7pF (4R7)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	5.0pF (5R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	5.6pF (5R6)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	6.0pF (6R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	6.8pF (6R8)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	7.0pF (7R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	8.0pF (8R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	8.2pF (8R2)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	9.0pF (9R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	10pF (100)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	12pF (120)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	15pF (150)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	18pF (180)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	22pF (220)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	27pF (270)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	33pF (330)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	39pF (390)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	47pF (470)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	56pF (560)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	68pF (680)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	82pF (820)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
	100pF (101)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
120pF (121)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A	
150pF (151)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A	
180pF (181)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A	
220pF (221)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A	
270pF (271)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A	
330pF (331)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A	
390pF (391)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B	
470pF (471)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B	
560pF (561)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B	
680pF (681)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B	
820pF (821)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B	
1,000pF (102)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B	
1,200pF (122)									X	X	X	X	X*	B	B	B	B	B	
1,500pF (152)									X	X	X	X	X*	B	B	B	B	B	
1,800pF (182)									X	X	X	X		B	B	B	B	B	
2,200pF (222)									X	X	X	X		B	B	B	B	B	
2,700pF (272)									X	X	X	X		D	D	D	D	D	
3,300pF (332)									X	X	X	X		D	D	D	D	D	
3,900pF (392)									X*	X*	X*	X*		D	D	D	D	D	
4,700pF (472)									X*	X*	X*	X*		D	D	D	D	D	
5,600pF (562)									X*	X*	X*	X*		D	D	D	D	D	
6,800pF (682)									X*	X*	X*	X*		D	D	D	D	D	
8,200pF (822)									X*	X*	X*	X*		D	D	D	D	D	
0.010uF (103)									X*	X*	X*	X*		D	D	D	D	D	
0.012uF (123)														T*	T*	T*	T*		
0.018uF (183)														D*	D*	D*	D*		
0.022uF (223)														D*	D*	D*	D*		

Capacitance Range—NPO Dielectric (1206, 1210, 1812 English sizes):

DIELECTRIC		NPO													
SIZE		1206					1210					1812			
RATED VOLTAGE (VDC)		10	16	25	50	100	10	16	25	50	100	16	50	100	
Capacitance	1.0pF (1R0)														
	1.2pF (1R2)	B	B	B	B	B									
	1.5pF (1R5)	B	B	B	B	B									
	1.8pF (1R8)	B	B	B	B	B									
	2.2pF (2R2)	B	B	B	B	B									
	2.7pF (2R7)	B	B	B	B	B									
	3.3pF (3R3)	B	B	B	B	B									
	3.9pF (3R9)	B	B	B	B	B									
	4.7pF (4R7)	B	B	B	B	B									
	5.6pF (5R6)	B	B	B	B	B									
	6.8pF (6R8)	B	B	B	B	B									
	8.2pF (8R2)	B	B	B	B	B									
	10pF (100)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	12pF (120)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	15pF (150)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	18pF (180)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	22pF (220)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	27pF (270)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	33pF (330)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	39pF (390)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	47pF (470)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	56pF (560)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	68pF (680)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	82pF (820)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	100pF (101)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	120pF (121)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	150pF (151)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	180pF (181)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	220pF (221)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	270pF (271)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	330pF (331)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	390pF (391)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	470pF (471)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	560pF (561)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	680pF (681)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	820pF (821)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	1,000pF (102)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	1,200pF (122)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	1,500pF (152)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
	1,800pF (182)	B	B	B	B	B	C	C	C	C	C	D	D	D	D
2,200pF (222)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
2,700pF (272)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
3,300pF (332)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
3,900pF (392)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
4,700pF (472)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
5,600pF (562)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
6,800pF (682)	C	C	C	C	C	C	C	C	C	C	D	D	D	D	
8,200pF (822)	D	D	D	D	D	C	C	C	C	C	D	D	D	D	
0.010µF (103)	D	D	D	D	D	C	C	C	C	C	D	D	D	D	
0.012µF (123)	P	P	P	P	P	D	D	D	D	D	D	D	D	D	
0.015µF (153)	P	P	P	P	P	D	D	D	D	D	D	D	D	D	
0.018µF (183)	P	P	P	P	P						D	D	D	D	
0.022µF (223)	P	P	P	P	P						D	D	D	D	
0.027µF (273)	P	P	P	P	P						D	D	D	D	
0.033µF (333)	P	P	P	P	P						D	D	D	D	
0.039µF (393)	P	P	P	P	P										
0.047µF (473)	J*	J*	J*	J*	J*										
0.056µF (563)	J*	J*	J*	J*	J*										
0.068µF (683)	G*	G*	G*	G*	G*										
0.082µF (823)	G*	G*	G*	G*	G*										
0.1µF (104)	G*	G*	G*	G*	G*										

Capacitance Range—X7R Dielectric (0201, 0402, 0603, 0805 English sizes):

DIELECTRIC		X7R																							
SIZE		0201					0402					0603					0805								
RATED VOLTAGE (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	6.3	10	16	25	50	100	
C a p a c i t a n c e	100pF (101)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	120pF (121)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	150pF (151)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	180pF (181)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	220pF (221)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	270pF (271)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	330pF (331)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	390pF (391)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	470pF (471)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	560pF (561)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	680pF (681)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	820pF (821)			L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	1,000pF (102)	L	L	L	L	L		N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	1,200pF (122)	L	L	L	L			N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	1,500pF (152)	L	L	L	L			N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	1,800pF (182)	L	L	L				N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	2,200pF (222)	L	L	L				N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	2,700pF (272)	L	L	L				N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	3,300pF (332)	L	L	L				N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	3,900pF (392)	L	L	L				N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	4,700pF (472)	L	L	L				N	N	N	N	N		S	S	S	S	S		B	B	B	B	B	
	5,600pF (562)	L	L					N	N	N	N			S	S	S	S	S		B	B	B	B	B	
	6,800pF (682)	L	L					N	N	N	N			S	S	S	S	S		B	B	B	B	B	
	8,200pF (822)	L	L					N	N	N	N			S	S	S	S	S		B	B	B	B	B	
	0.010μF (103)	L	L	L				N	N	N	N			S	S	S	S	S		B	B	B	B	B	
	0.012μF (123)							N	N	N				S	S	S	S	X		B	B	B	B	B	
	0.015μF (153)							N	N	N				S	S	S	S	X		B	B	B	B	B	
	0.018μF (183)							N	N	N				S	S	S	S	X		B	B	B	B	B	
	0.022μF (223)							N	N	N	N			S	S	S	S	X		B	B	B	B	B	
	0.027μF (273)							N	N	N				S	S	S	S	X		B	B	B	B	D	
0.033μF (333)							N	N	N	N			S	S	S	X	X		B	B	B	B	D		
0.039μF (393)							N	N	N				S	S	S	X	X		B	B	B	B	D		
0.047μF (473)							N	N	N	N			S	S	S	X	X		B	B	B	B	D		
0.056μF (563)							N	N					S	S	S	X	X		B	B	B	B	D		
0.068μF (683)							N	N		N			S	S	S	X	X		B	B	B	B	D		
0.082μF (823)							N	N					S	S	S	X	X		B	B	B	B	D		
0.10μF (104)						N	N	N	N	N			S	S	S	X	X		B	B	B	B	D		
0.12μF (124)													S	S	X				B	B	B	D			
0.15μF (154)													S	S	X				D	D	D	D			
0.18μF (184)													S	S	X				D	D	D	D			
0.22μF (224)						N	N	N	N				S	S	X	X			D	D	D	D	T		
0.27μF (274)													X	X	X	X			D	D	D	I			
0.33μF (334)													X	X	X	X			D	D	D	I			
0.39μF (394)													X	X	X	X			D	D	D	I			
0.47μF (474)						N	N						X	X	X	X	X		D	D	D	I	I		
0.56μF (564)													X	X	X				D	D	D				
0.68μF (684)													X	X	X				D	D	D				
0.82μF (824)													X	X	X				D	D	D				
1.0μF (105)						N							X	X	X	X	X		D	D	D	I			

Capacitance Range—X7R Dielectric (1206, 1210, 1812 English sizes):

DIELECTRIC		X7R																	
		1206							1210						1812				
SIZE		6.3	10	16	25	35	50	100	6.3	10	16	25	50	100	10	16	25	50	100
RATED VOLTAGE (VDC)		6.3	10	16	25	35	50	100	6.3	10	16	25	50	100	10	16	25	50	100
C0G	100pF (101)																		
	120pF (121)																		
	150pF (151)		B	B	B		B	B											
	180pF (181)		B	B	B		B	B											
	220pF (221)		B	B	B		B	B											
	270pF (271)		B	B	B		B	B											
	330pF (331)		B	B	B		B	B											
	390pF (391)		B	B	B		B	B											
	470pF (471)		B	B	B		B	B											
	560pF (561)		B	B	B		B	B											
	680pF (681)		B	B	B		B	B											
	820pF (821)		B	B	B		B	B											
	1,000pF (102)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	1,200pF (122)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	1,500pF (152)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	1,800pF (182)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	2,200pF (222)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	2,700pF (272)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	3,300pF (332)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	3,900pF (392)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	4,700pF (472)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	5,600pF (562)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	6,800pF (682)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	8,200pF (822)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.010μF (103)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.012μF (123)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.015μF (153)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.018μF (183)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.022μF (223)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.027μF (273)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.033μF (333)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.039μF (393)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.047μF (473)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.056μF (563)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
	0.068μF (683)		B	B	B		B	B		C	C	C	C	C	D	D	D	D	D
0.082μF (823)		B	B	B		B	D		C	C	C	C	C	D	D	D	D	D	
0.10μF (104)		B	B	B		B	D		C	C	C	C	C	D	D	D	D	D	
0.12μF (124)		B	B	B		B	D		C	C	C	C	C	D	D	D	D	D	
0.15μF (154)		C	C	C		C	G		C	C	C	C	D	D	D	D	D	D	
0.18μF (184)		C	C	C		C	G		C	C	C	C	D	D	D	D	D	D	
0.22μF (224)		C	C	C		C	G		C	C	C	C	D	D	D	D	D	D	
0.27μF (274)		C	C	C		D	G		C	C	C	C	G	D	D	D	D	D	
0.33μF (334)		C	C	C		D	G		C	C	C	D	G	D	D	D	D	D	
0.39μF (394)		C	C	J		P	G		C	C	C	D	M	D	D	D	D	D	
0.47μF (474)		J	J	J		P	G		C	C	C	D	M	D	D	D	D	K	
0.56μF (564)		J	J	J		P	P		D	D	D	D	M	D	D	D	D	K	
0.68μF (684)		J	J	J		P	P		D	D	D	D	K	D	D	D	K	K	
0.82μF (824)		J	J	J		P	P		D	D	D	D	K	D	D	D	K	K	
1.0μF (105)		J	J	J		P	P		D	D	D	D	K	D	D	D	K	K	

Capacitance Range—Y5V Dielectric (0402, 0603, 0805 English sizes):

DIELECTRIC		Y5V															
SIZE		0402					0603					0805					
RATED VOLTAGE (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	100
Capacitance	0.010µF (103)		N	N	N	N		S	S	S	S		A	A	A	A	B
	0.015µF (153)		N	N	N	N		S	S	S	S		A	A	A	A	B
	0.022µF (223)		N	N	N	N		S	S	S	S		A	A	A	A	B
	0.033µF (333)		N	N	N	N		S	S	S	S		A	A	A	A	B
	0.047µF (473)		N	N	N			S	S	S	S		A	A	A	A	B
	0.068µF (683)		N	N	N			S	S	S	S		A	A	A	A	B
	0.10µF (104)		N	N	N			S	S	S	S		A	A	A	A	B
	0.15µF (154)		N	N				S	S	S	S		A	A	A	A	
	0.22µF (224)	N	N	N				S	S	S	S		A	A	A	A	
	0.33µF (334)	N	N	N				S	S	S	X		B	B	B	B	
	0.47µF (474)	N	N	N				S	S	X	X		B	B	B	B	
	0.68µF (684)	N						S	X	X			B	B	D	D	
	1.0µF (105)	N	N					S	X	X			B	B	D	D	

Capacitance Range—Y5V Dielectric (1206, 1210, 1812 English sizes):

DIELECTRIC		Y5V																		
SIZE		1206					1210					1812								
RATED VOLTAGE (VDC)		6.3	10	16	25	50	100	6.3	10	16	25	35	50	100	10	16	25	50	100	
Capacitance	0.010µF (103)		B	B	B	B	B							C					D	
	0.015µF (153)		B	B	B	B	B							C					D	
	0.022µF (223)		B	B	B	B	B							C					D	
	0.033µF (333)		B	B	B	B	B							C					D	
	0.047µF (473)		B	B	B	B	B							C					D	
	0.068µF (683)		B	B	B	B	B							C					D	
	0.10µF (104)		B	B	B	B	B		C	C	C			C	C	D	D	D	D	D
	0.15µF (154)		B	B	B	B	C		C	C	C			C	C	D	D	D	D	D
	0.22µF (224)		B	B	B	B	C		C	C	C			C	C	D	D	D	D	D
	0.33µF (334)		B	B	B	B			C	C	C			C	C	D	D	D	D	D
	0.47µF (474)		B	B	B	B			C	C	C			C		D	D	D	D	D
	0.68µF (684)		B	B	B	B			C	C	C			C		D	D	D	D	D
	1.0µF (105)		C	C	C	C			C	C	C			C		D	D	D	D	D

Capacitance Range—X5R Dielectric (0201, 0402, 0603 English sizes):

Dielectric		X5R														
Size		0201					0402					0603				
Rated Voltage (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50
C a p a c i t a n c e	100pF (101)			L	L	L										
	120pF (121)			L	L	L										
	150pF (151)			L	L	L										
	180pF (181)			L	L	L										
	220pF (221)			L	L	L										
	270pF (271)			L	L	L										
	330pF (331)			L	L	L										
	390pF (391)			L	L	L										
	470pF (471)			L	L	L										
	560pF (561)			L	L	L										
	680pF (681)			L	L	L										
	820pF (821)			L	L	L										
	1,000pF (102)		L	L	L	L										
	1,500pF (152)		L	L												
	2,200pF (222)		L	L												
	2,700pF (272)		L	L												
	3,300pF (332)		L	L												
	4,700pF (472)		L	L												
	6,800pF (682)		L													
	0.010µF (103)	L	L	L	L											
	0.015µF (153)	L	L													
	0.022µF (223)	L	L													
	0.027µF (273)	L	L						N							
	0.033µF (333)	L	L						N							
	0.039µF (393)	L	L						N							
	0.047µF (473)	L	L						N							
	0.056µF (563)	L	L					N	N							
	0.068µF (683)	L	L					N	N							
	0.082µF (823)	L	L				N	N	N							
	0.10µF (104)	L	L	L	L		N	N	N	N	N					
0.15µF (154)						N	N	N	N							
0.22µF (224)	L	L				N	N	N	N	N			X	X		
0.27µF (274)												X	X	X		
0.33µF (334)						N	N				X	X	X	X		
0.39µF (394)												X	X	X		
0.47µF (474)	L					N	N	E	E	E	X	X	X	X	X	
0.68µF (684)						N	N				X	X	X	X		
0.82µF (824)											X	X	X			
1.0µF (105)	L	L*				N	N	N	N		X	X	X	X	X	

Capacitance Range—X5R Dielectric (0805, 1206, 1210 English sizes):

Dielectric		X5R																
Size		0805					1206					1210						
Rated Voltage (VDC)		4	6.3	10	16	25	50	6.3	10	16	25	50	4	6.3	10	16	25	50
Capacitance	1.0µF (105)			D	D	D	I											

Packaging Type and Quantity:

Size	Thickness (mm)/Symbol		Paper tape		Plastic tape	
			7" reel	13" reel	7" reel	13" reel
0201 (0603)	0.30±0.03	L	15,000	70,000	-	-
	0.30±0.05	L	15,000	-	-	-
	0.30±0.09	L	15,000	-	-	-
0402 (1005)	0.50±0.05	N	10,000	50,000	-	-
	0.50+0.02/-0.05	Q	10,000	50,000	-	-
	0.50±0.20	E	10,000	-	-	-
0603 (1608)	0.50±0.10	H	4,000	-	-	-
	0.80±0.07	S	4,000	15,000	-	-
	0.80+0.15/-0.10	X	4,000	15,000	-	-
0805 (2012)	0.50±0.10	H	4,000	15,000	-	-
	0.60±0.10	A	4,000	15,000	-	-
	0.80±0.10	B	4,000	15,000	-	-
	0.85±0.10	T	4,000	15,000	-	-
	1.25±0.10	D	-	-	3,000	10,000
	1.25±0.20	I	-	-	3,000	10,000
1206 (3216)	0.80±0.10	B	4,000	15,000	-	-
	0.85±0.10	T	4,000	15,000	-	-
	0.95±0.10	C	-	-	3,000	10,000
	1.15±0.15	J	-	-	3,000	10,000
	1.25±0.10	D	-	-	3,000	10,000
	1.60±0.20	G	-	-	2,000	10,000
	1.60+0.30/-0.10	P	-	-	2,000	9,000
1210 (3225)	0.85±0.10	T	-	-	3,000	10,000
	0.95±0.10	C	-	-	3,000	10,000
	1.25±0.10	D	-	-	3,000	10,000
	1.60±0.20	G	-	-	2,000	-
	2.00±0.20	K	-	-	1,000	6,000
	2.50±0.30	M	-	-	1,000	6,000
1812 (4532)	1.25±0.10	D	-	-	1,000	5,000
	1.60±0.20	G	-	-	1,000	-
	2.00±0.20	K	-	-	1,000	-
	2.50±0.30	M	-	-	500	3,000
	2.80±0.30	U	-	-	500	-

1. The letter in the cell is corresponding to the symbol of product thickness as reflected in the dimensional table.
2. The letter in cell with " * " mark is expressed capacitance tolerance "J" (±5%) only for NPO dielectric and "K" (±10%) for other dielectrics
3. For more information about products with special capacitance or other data, please contact the factory.

Reliability Test Conditions and Requirements:

Item	Test Condition	Requirements				
Visual and Mechanical	---	*No remarkable defect. *Dimensions to conform to individual specification sheet				
Capacitance	Class I: (NP0) ≤1000pF, 1.0±0.2Vrms, 1MHz ± 10% >1000pF, 1.0 1KHz±10% Class II: (X7R, X5R, Y5V) C≤10μF, 1.0±0.2Vrms, 1KHz±10%** C>10μF, 0.5±0.2Vrms, 120Hz±20%	*Shall not exceed the limits given in the detailed spec.				
Q/D.F. (Dissipation Factor)	**Test condition: 0.5±0.2Vrms, 1KHz±10% X7R: 0805=106(6.3V), 0603/475(6.3V) X5R: 01R5≥103, 0201≥224 (6.3V, 10V, 16V) #1, 0402≥475 (6.3V, 16V), 0402≥225 (10V), TT18X≥475(10V), TT15X series #1 Excluding X5R/0201/105(6.3V); 225 (10V), (1.0±0.2Vrms, 1KHz±10%) *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	NP0: Cap≥30pF, Q≥1000; Cap<30pF, Q≥400+20C X7R, X5R:				
		Rated Vol.	D.F. ≤	Exception of D.F. ≤		
		≥100V	≤2.5%	≤3%	1206≥0.47μF	
				≤5%	0805>0.1μF; 0603≥0.068μF; 1206>1μF; 1210≥2.2μF; TT series	
				≤10%	0805>0.22μF; 1210≥3.3μF	
		50V	≤2.5%	≤3%	0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF	
				≤5%	0201≥0.01μF; 1210≥4.7μF	
				≤10%	0402≥0.01μF; 0603>0.1μF; 0805≥1μF; 1206≥2.2μF; 1210≥10μF; TT series	
		35V	≤3.5%	≤10%	0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF	
				≤5%	0201≥0.01μF; 0805≥1μF; 1210≥10μF	
		25V	≤3.5%	≤7%	0603≥0.33μF; 1206≥4.7μF	
				≤10%	0201≥0.1μF; 0402≥0.10μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥6.8μF; 1210≥22μF; TT series	
				≤12.5%	0402≥0.47μF	
				≤5%	0201≥0.01μF; 0402≥0.033μF; 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF	
		16V	≤3.5%	≤10%	0201≥0.1μF(0201/X7R≥0.022μF); 0402≥0.22μF; 0603≥0.68μ; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series	
				≤15%	0201≥0.012μF; 0402≥0.33μF(0402/X7R≥0.22μF); TT series 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF: 01R5	
		10V	≤5%	≤15%	0201≥0.1μF; 0402≥1μF; 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF; TT series	
				≤20%	0402≥2.2μF	
		6.3V	≤10%	---	---	
				---	---	
4V	≤15%	---	---			
Y5V:						
Rated Vol	D.F. ≤	Exception of D.F. ≤				
≥50V	≤5%	≤7%	0603≥0.1μF;0805≥0.47μF;1206≥4.7μF;TT series			
		≤12.5%	1210≥6.8μF			
35V	≤7%	---	---			
25V	≤5%	≤7%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF;1206≥1μF;1210≥4.7μF			
		≤9%	0402≤0.068μF;0603≤0.47μF;1206≥4.7μF;1210≤22μF;TT series			
16V (C<1.0μF)	≤7%	≤9%	0402≥0.068μF;0603≤0.68μF			
		≤12.5%	0402≤0.22μF			
16V (C≥1.0μF)	≤9%	≤12.5%	0603≥2.2μF;0805≤3.3μF;1206≥10μF;1210≤22μF;1812≥47μF;TT series			
10V	≤12.5%	≤20%	0402≥0.47μF			
6.3V	≤20%	---	---			

Reliability Test Conditions and Requirements Continued:

Item	Test Condition	Requirements											
Dielectric Strength	*To apply voltage ($\leq 100V$) 250% *Duration: 1 to 5 sec. *Charge and discharge current less than 50mA.	*No evidence of damage or flash over during test.											
Insulation Resistance	To apply rated voltage for MAX. 120 sec. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2hrs at room temp.	10GΩ or RxC $\geq 500\Omega\cdot F$ whichever is smaller Class II (X7R, X5R, Y5V):											
		<table border="1"> <thead> <tr> <th>Rated Voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: All X7R</td> <td rowspan="6">10FΩ or RxC $\geq 100\Omega\cdot F$ whichever is smaller</td> </tr> <tr> <td>50V: 0402 $> 0.01\mu F$; 0603 $\geq 1\mu F$; 0805 $\geq 1\mu F$; 1206 $\geq 4.7\mu F$; 1210 $\geq 4.7\mu F$</td> </tr> <tr> <td>35V: 0805 $\geq 2.2\mu F$; 1206 $\geq 2.2\mu F$; 1210 $\geq 10\mu F$</td> </tr> <tr> <td>25V: 0402 $\geq 1\mu F$; 0603 $\geq 2.2\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 10\mu F$; 1210 $\geq 10\mu F$</td> </tr> <tr> <td>16V: 0201 $\geq 0.1\mu F$; 0402 $\geq 0.22\mu F$; 0603 $\geq 1\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 10\mu F$; 1210 $\geq 4.7\mu F$</td> </tr> <tr> <td>10V: 0201 $\geq 47nF$; 0402 $\geq 0.47\mu F$; 0603 $\geq 0.47\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 4.7\mu F$; 1210 $\geq 4.7\mu F$</td> </tr> <tr> <td>6.3V; 4V; TT series; Size ≥ 1812</td> <td></td> </tr> </tbody> </table>	Rated Voltage	Insulation Resistance	100V: All X7R	10FΩ or RxC $\geq 100\Omega\cdot F$ whichever is smaller	50V: 0402 $> 0.01\mu F$; 0603 $\geq 1\mu F$; 0805 $\geq 1\mu F$; 1206 $\geq 4.7\mu F$; 1210 $\geq 4.7\mu F$	35V: 0805 $\geq 2.2\mu F$; 1206 $\geq 2.2\mu F$; 1210 $\geq 10\mu F$	25V: 0402 $\geq 1\mu F$; 0603 $\geq 2.2\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 10\mu F$; 1210 $\geq 10\mu F$	16V: 0201 $\geq 0.1\mu F$; 0402 $\geq 0.22\mu F$; 0603 $\geq 1\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 10\mu F$; 1210 $\geq 4.7\mu F$	10V: 0201 $\geq 47nF$; 0402 $\geq 0.47\mu F$; 0603 $\geq 0.47\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 4.7\mu F$; 1210 $\geq 4.7\mu F$	6.3V; 4V; TT series; Size ≥ 1812	
		Rated Voltage	Insulation Resistance										
		100V: All X7R	10FΩ or RxC $\geq 100\Omega\cdot F$ whichever is smaller										
		50V: 0402 $> 0.01\mu F$; 0603 $\geq 1\mu F$; 0805 $\geq 1\mu F$; 1206 $\geq 4.7\mu F$; 1210 $\geq 4.7\mu F$											
		35V: 0805 $\geq 2.2\mu F$; 1206 $\geq 2.2\mu F$; 1210 $\geq 10\mu F$											
		25V: 0402 $\geq 1\mu F$; 0603 $\geq 2.2\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 10\mu F$; 1210 $\geq 10\mu F$											
16V: 0201 $\geq 0.1\mu F$; 0402 $\geq 0.22\mu F$; 0603 $\geq 1\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 10\mu F$; 1210 $\geq 4.7\mu F$													
10V: 0201 $\geq 47nF$; 0402 $\geq 0.47\mu F$; 0603 $\geq 0.47\mu F$; 0805 $\geq 2.2\mu F$; 1206 $\geq 4.7\mu F$; 1210 $\geq 4.7\mu F$													
6.3V; 4V; TT series; Size ≥ 1812													
Temperature Coefficient	With no electrical load.	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>NP0</td> <td>Within ± 30ppm/°C</td> </tr> <tr> <td>X7R</td> <td>Within $\pm 15\%$</td> </tr> <tr> <td>X5R</td> <td>Within $\pm 15\%$</td> </tr> <tr> <td>Y5R</td> <td>Within +30%/-80%</td> </tr> </tbody> </table>	T.C.	Capacitance Change	NP0	Within ± 30 ppm/°C	X7R	Within $\pm 15\%$	X5R	Within $\pm 15\%$	Y5R	Within +30%/-80%	
	T.C.		Capacitance Change										
	NP0		Within ± 30 ppm/°C										
	X7R		Within $\pm 15\%$										
	X5R		Within $\pm 15\%$										
	Y5R		Within +30%/-80%										
	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp</th> </tr> </thead> <tbody> <tr> <td>NP0</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X5R</td> <td>-55~85°C at 25°C</td> </tr> <tr> <td>Y5R</td> <td>-25~85°C at 20°C</td> </tr> </tbody> </table>		T.C.	Operating Temp	NP0	-55~125°C at 25°C	X7R	-55~125°C at 25°C	X5R	-55~85°C at 25°C	Y5R	-25~85°C at 20°C	
	T.C.		Operating Temp										
	NP0		-55~125°C at 25°C										
	X7R		-55~125°C at 25°C										
	X5R		-55~85°C at 25°C										
	Y5R		-25~85°C at 20°C										
	*Before Initial Measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2hrs at room temp. *Measurement voltage for Class II:												
	<table border="1"> <thead> <tr> <th>01005</th> <th>0201</th> </tr> </thead> <tbody> <tr> <td>Cap $\leq 0.01\mu F$: 0.5V</td> <td>Cap $< 0.1\mu F$: 1V</td> </tr> <tr> <td>Cap $> 0.01\mu F$: 0.2V</td> <td>0.1 $\mu F \leq$ Cap $< 1\mu F$: 0.2V</td> </tr> <tr> <td></td> <td>Cap $\geq 1\mu F$: 0.1V</td> </tr> </tbody> </table>		01005	0201	Cap $\leq 0.01\mu F$: 0.5V	Cap $< 0.1\mu F$: 1V	Cap $> 0.01\mu F$: 0.2V	0.1 $\mu F \leq$ Cap $< 1\mu F$: 0.2V		Cap $\geq 1\mu F$: 0.1V			
01005	0201												
Cap $\leq 0.01\mu F$: 0.5V	Cap $< 0.1\mu F$: 1V												
Cap $> 0.01\mu F$: 0.2V	0.1 $\mu F \leq$ Cap $< 1\mu F$: 0.2V												
	Cap $\geq 1\mu F$: 0.1V												
<table border="1"> <thead> <tr> <th>0402</th> <th>0603</th> </tr> </thead> <tbody> <tr> <td>Cap $< 1\mu F$: 1V</td> <td>Cap $\leq 1\mu F$: 1V</td> </tr> <tr> <td>Cap = 1 μF: 0.5V</td> <td>1 $\mu F <$ Cap $\leq 4.7\mu F$: 0.5V</td> </tr> <tr> <td>1 $\mu F <$ Cap $< 10\mu F$: 0.2V</td> <td>Cap $> 4.7\mu F$: 0.2V</td> </tr> <tr> <td>Cap $\geq 10\mu F$: 0.1V</td> <td></td> </tr> </tbody> </table>	0402	0603	Cap $< 1\mu F$: 1V	Cap $\leq 1\mu F$: 1V	Cap = 1 μF : 0.5V	1 $\mu F <$ Cap $\leq 4.7\mu F$: 0.5V	1 $\mu F <$ Cap $< 10\mu F$: 0.2V	Cap $> 4.7\mu F$: 0.2V	Cap $\geq 10\mu F$: 0.1V				
0402	0603												
Cap $< 1\mu F$: 1V	Cap $\leq 1\mu F$: 1V												
Cap = 1 μF : 0.5V	1 $\mu F <$ Cap $\leq 4.7\mu F$: 0.5V												
1 $\mu F <$ Cap $< 10\mu F$: 0.2V	Cap $> 4.7\mu F$: 0.2V												
Cap $\geq 10\mu F$: 0.1V													
<table border="1"> <thead> <tr> <th>0805</th> <th>1206/1210</th> </tr> </thead> <tbody> <tr> <td>Cap $< 10\mu F$: 1V</td> <td>Cap $\leq 10\mu F$: 1V</td> </tr> <tr> <td>Cap = 10 μF: 0.5V</td> <td>10 $\mu F <$ Cap $\leq 100\mu F$: 0.5V</td> </tr> <tr> <td>Cap $> 10\mu F$: 0.2V</td> <td>Cap $> 100\mu F$: 0.2V</td> </tr> </tbody> </table>	0805	1206/1210	Cap $< 10\mu F$: 1V	Cap $\leq 10\mu F$: 1V	Cap = 10 μF : 0.5V	10 $\mu F <$ Cap $\leq 100\mu F$: 0.5V	Cap $> 10\mu F$: 0.2V	Cap $> 100\mu F$: 0.2V					
0805	1206/1210												
Cap $< 10\mu F$: 1V	Cap $\leq 10\mu F$: 1V												
Cap = 10 μF : 0.5V	10 $\mu F <$ Cap $\leq 100\mu F$: 0.5V												
Cap $> 10\mu F$: 0.2V	Cap $> 100\mu F$: 0.2V												
Adhesive Strength of Termination	*Pressurizing force: 1N (0201) and 5N (≤ 0603) and 10N (> 0603) *Test time: 10±1 sec.	*No remarkable damage or removal of the terminations											
Vibration Resistance	*Vibration frequency: 10~55 Hz/min. *Total amplitude: 1.5mm *Test time: 6hrs. (two hrs each in three mutually perpendicular directions) *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Cap./DF(Q) Measurement to be made after de-aging at 150°C for 1 hr then set for 24±2 hrs at room temp.												

Reliability Test Conditions and Requirements Continued:

Item	Test Condition	Requirements															
Solderability	*Solder temperature: 235±5°C *Dipping time: 2±0.5 sec.	95% min. coverage of all metalized area.															
Bending Test	*The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Measurement to be made after keeping at room temp. for 24±2hrs.	*No remarkable damage. *Cap change: NP0: within ±5% or 0.5pF whichever is larger X7R, X5R: within ±12.5% Y5V: within ±30% (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)															
Resistance to Soldering Heat	*Solder temperature: 260±5°C *Dipping time: 10±1 sec *Preheating: 120 to 150°C for 1 minute before immersing the capacitor in a eutectic solder. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Cap./DF(Q)/I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	*No remarkable damage. *Cap change: NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R: within ±7.5% Y5V: within ±20%*Q/D.F., I.R. and dielectric strength. To meet initial requirements. *25% max. leaching on each edge.															
Temperature Cycle	<table border="1" data-bbox="243 1302 724 1491"> <thead> <tr> <th data-bbox="243 1302 316 1344">Step</th> <th data-bbox="316 1302 576 1344">Temp. (°C)</th> <th data-bbox="576 1302 724 1344">Time (min)</th> </tr> </thead> <tbody> <tr> <td data-bbox="243 1344 316 1386">1</td> <td data-bbox="316 1344 576 1386">Min. operating temp. +0/-3</td> <td data-bbox="576 1344 724 1386">30±3</td> </tr> <tr> <td data-bbox="243 1386 316 1428">2</td> <td data-bbox="316 1386 576 1428">Room temp.</td> <td data-bbox="576 1386 724 1428">2~3</td> </tr> <tr> <td data-bbox="243 1428 316 1470">3</td> <td data-bbox="316 1428 576 1470">Max. operating temp. +3/-0</td> <td data-bbox="576 1428 724 1470">30±3</td> </tr> <tr> <td data-bbox="243 1470 316 1491">4</td> <td data-bbox="316 1470 576 1491">Room temp.</td> <td data-bbox="576 1470 724 1491">2~3</td> </tr> </tbody> </table> <p data-bbox="243 1491 724 1976"> *Conduct the five cycles according to the temperatures and time. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Cap./DF(Q)/I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. </p>	Step	Temp. (°C)	Time (min)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	*No remarkable damage. *Cap change: NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R: within ±7.5% Y5V: within ±20% *Q/D.F., I.R. and dielectric strength: To meet initial requirements
Step	Temp. (°C)	Time (min)															
1	Min. operating temp. +0/-3	30±3															
2	Room temp.	2~3															
3	Max. operating temp. +3/-0	30±3															
4	Room temp.	2~3															

Reliability Test Conditions and Requirements Continued:

Item	Test Condition	Requirements			
Humidity (Damp Heat) Steady State	*No remarkable damage. *Cap change: NP0: within ±5% or 0.5pF whichever is larger X7R, X5R: ≥10V**, within ±12.5%; ≤6.3V within ±25%; TT series **10V: 0603 ≥ 4.7µF; 0402 ≥ 1µF; 0201 ≥ 0.1µF, within ±25%; Y5V: ≥10V, within ±30%; ≤6.3V, within +30/-40% *Q/D.F. value: NP0: More than 30pF Q≥350, 10pF≤C≤30pF, Q≥275+2.5C Less than 10pF Q≥200+10C	*No remarkable damage. *Cap change: NP0: within ±5% or 0.5pF whichever is larger X7R, X5R: ≥10V**, within ±12.5%; ≤6.3V within ±25%; TT series & C≥1µF, within ±25% **10V: 0603 ≥ 4.7µF; 0402 ≥ 1µF; 0201 ≥ 0.1µF, within ±25%; Y5V: ≥10V, within ±30%; ≤6.3V, within +30/-40% *Q/D.F. value: NP0: More than 30pF Q≥350, 10pF≤C≤30pF, Q≥275+2.5C Less than 10pF Q≥200+10C X7R, X5R:			
		Rated Vol.	D.F. ≤	Exception of D.F. ≤	
		≥100V	≤3%	≤6%	1206≥0.47µF
				≤7.5%	0805>0.1µF;0603≥0.068µF;1206>1µF;1210≥2.2µF; TT series
				≤20%	0805>0.22µ;1210≥3.3µF
				≤6%	0201(50V);0603≥0.047µF;0805≥0.18µF;1206≥0.47µF
		50V	≤3%	≤10%	0201≥0.01µF;1210≥4.7µF
				≤20%	0402≥0.01µF;0603>0.1µF;0805≥1µF;1206≥2.2µF;1210≥10µF; TT series
				≤20%	0603≥1µF;0805≥2.2µF;1206≥2.2µF;1210≥10µF
		25V	≤5%	≤10%	0201≥0.01µF;0805≥1µF;1210≥10µF
				≤14%	0603≥0.33µ;1206≥4.7µF
				≤15%	0201≥0.1µF;0402≥0.10µF;0603≥0.47µ;0805≥2.2µF;1206≥6.8µF;1210≥22µF; TT series
				≤20%	0402≥0.47µF
		16V	≤5%	≤10%	0603≥0.15µF;0805≥0.68µF;1206≥2.2µF;1210≥4.7µF
				≤15%	0201≥0.01µF(0201/X7R≥0.022µF);0402≥0.033µF;0603≥0.68µF;0805≥2.2;1206≥4.7µF;1210≥22µF; TT series
		10V	≤7.5%	≤15%	0201≥0.012µF;0402≥0.33µF(0402/X7R≥0.22µF);0603≥0.33µF;0805≥2.2µF;1206≥2.2µF;1210≥22µF
				≤20%	0201≥0.1µF;0402≥1µF; TT series; 01R5
		6.3V	≤15%	≤30%	0201≥0.1µF;0402≥1µF;0603≥10µF;0805≥4.7µF;1206≥47µF1210≥100µF; TT series
		4V	≤20%	---	---
		Y5V:			
		Rated Vol.	D.F. ≤	Exception of D.F. ≤	
		≥50V	≤7.5%	≤10%	0603≥0.1µF;0805≥0.47µF;1206≥4.7µF
				≤20%	1210≥6.8µF
		35V	≤10%	---	---
		25V	≤7.5%	≤10%	0402≥0.047µF;0603≥0.1µF;0805≥0.33µF;1206≥1µF;1210≥4.7µF
				≤15%	0402≥0.068µF;0603≥0.47µF;1206≥4.7µF;1210≥22µF
		16V (C≥1.0µF)	≤10%	≤12.5%	0402≥0.068µF;0603≥0.68µF
≤20%	0402≥0.22µF				
16V (C≥1.0µF)	≤12.5%	≤20%	0603≥2.2µF;0805≥3.3µF;1206≥10µF;1210≥22µF;1812≥47µF		
10V	≤20%	≤30%	0402≥0.47µF		
6.3V	≤30%	---	---		
*1.R.:≥10V, 1GΩ or 50 Ω-F whichever is smaller Class II (X7R, X5R, Y5V)					
Rated Voltage			Insulation Resistance		
100V: All X7R; 1210≥3.3µF			1GΩ or RxC ≥ 10 Ω-F whichever is smaller		
50V: 0402>0.01µF;0603≥1µF;0805≥1µF;1206≥4.7µF;1210≥4.7µF					
35V: 0603≥1µF;0805≥2.2µF;1206≥2.2µF;1210≥10F					
25V: 0201≥0.1µF;0402≥0.22µF;0603≥2.2µF;0805≥2.2µF;1206≥10µF;1210≥10µF					
16V:0201≥0.1µF;0402≥0.22µF;0603≥1µF;0805≥2.2µF1206≥10µF;1210≥47µF					
10V:1201≥47nF;0402≥0.47µF;0603≥0.47µF; 0805≥2.2µF;1206≥4.7µF;1210≥47µF					
6.3V ; 4V ; TT series ; Size≥1812					

Reliability Test Conditions and Requirements Continued:

Item	Test Condition	Requirements																																																				
Humidity (Damp Heat) Load	*Test temp.: 40±2°C *Humidity: 90~95%RH *Test time: 500+24/-0hrs *To apply voltage: Rated voltage (MAX. 500V) *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Cap./DF(Q)/I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	*No remarkable damage. *Cap change: NP0: within ±7.5% or 0.75pF whichever is larger X7R, X5R: ≥10V**, within ±12.5%; ≤6.3V within ±25%; TT series & C≥1μF, within ±25% **10V: 0603 ≥ 4.7μF; 0402 ≥ 1μF; 0201 ≥ 0.1μF, within ±25%; Y5V: ≥10V, within ±30%; ≤6.3V, within +30/-40% *Q/D.F. value: NP0: C≥30pF, Q≥200; C<30pF, Q≥100+10/3C X7R, X5R:																																																				
		<table border="1"> <thead> <tr> <th>Rated Vol.</th> <th>D.F. ≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td rowspan="3">≥100V</td> <td rowspan="3">≤3%</td> <td>≤6%</td> <td>1206≥0.47μF</td> </tr> <tr> <td>≤7.5%</td> <td>0805>0.1μF,0603≥0.068μF,1206>1μF;1210≥2.2μF; TT series</td> </tr> <tr> <td>≤20%</td> <td>0805>0.22μ;1210≥3.3μF</td> </tr> <tr> <td rowspan="3">50V</td> <td rowspan="3">≤3%</td> <td>≤6%</td> <td>0201(50V);0603≥0.047μF;0805≥0.18μF;1206≥0.47μF</td> </tr> <tr> <td>≤10%</td> <td>0201≥0.01μF;1210≥4.7μF</td> </tr> <tr> <td>≤20%</td> <td>0402≥0.01μF;0603>0.1μF;0805≥1μF;1206≥2.2μF;1210≥10μF; TT series</td> </tr> <tr> <td>35V</td> <td>≤5%</td> <td>≤20%</td> <td>0603≥1μF;0805≥2.2μF;1206≥2.2μF;1210≥10μF</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">≤5%</td> <td>≤10%</td> <td>0201≥0.01μF;0805≥1μF;1210≥10μF</td> </tr> <tr> <td>≤14%</td> <td>0603≥0.33μ;1206≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0201≥0.1μF;0402≥0.10μF;0603≥0.47μ;0805≥2.2μF;1206≥6.8μF;1210≥22μF; TT series</td> </tr> <tr> <td>≤20%</td> <td>0402≥0.47μF</td> </tr> <tr> <td>16V</td> <td>≤5%</td> <td>≤10%</td> <td>0603≥0.15μF;0805≥0.68μF;1206≥2.2μ;1210≥4.7μF</td> </tr> <tr> <td rowspan="2">10V</td> <td rowspan="2">≤7.5%</td> <td>≤15%</td> <td>0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF);0603≥0.33μF0805≥2.2μF;1206≥2.2μF;1210≥22μF</td> </tr> <tr> <td>≤20%</td> <td>0201≥0.1μF;0402≥1μF; TT series; 01R5</td> </tr> <tr> <td>6.3V</td> <td>≤15%</td> <td>≤30%</td> <td>0201≥0.1μF;0402≥1μF;0603≥10μF;0805≥4.7μF;1206≥47μF1210≥100μF; TT series</td> </tr> <tr> <td>4V</td> <td>≤20%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated Vol.	D.F. ≤	Exception of D.F. ≤		≥100V	≤3%	≤6%	1206≥0.47μF	≤7.5%	0805>0.1μF,0603≥0.068μF,1206>1μF;1210≥2.2μF; TT series	≤20%	0805>0.22μ;1210≥3.3μF	50V	≤3%	≤6%	0201(50V);0603≥0.047μF;0805≥0.18μF;1206≥0.47μF	≤10%	0201≥0.01μF;1210≥4.7μF	≤20%	0402≥0.01μF;0603>0.1μF;0805≥1μF;1206≥2.2μF;1210≥10μF; TT series	35V	≤5%	≤20%	0603≥1μF;0805≥2.2μF;1206≥2.2μF;1210≥10μF	25V	≤5%	≤10%	0201≥0.01μF;0805≥1μF;1210≥10μF	≤14%	0603≥0.33μ;1206≥4.7μF	≤15%	0201≥0.1μF;0402≥0.10μF;0603≥0.47μ;0805≥2.2μF;1206≥6.8μF;1210≥22μF; TT series	≤20%	0402≥0.47μF	16V	≤5%	≤10%	0603≥0.15μF;0805≥0.68μF;1206≥2.2μ;1210≥4.7μF	10V	≤7.5%	≤15%	0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF);0603≥0.33μF0805≥2.2μF;1206≥2.2μF;1210≥22μF	≤20%	0201≥0.1μF;0402≥1μF; TT series; 01R5	6.3V	≤15%	≤30%	0201≥0.1μF;0402≥1μF;0603≥10μF;0805≥4.7μF;1206≥47μF1210≥100μF; TT series	4V	≤20%	---	---
		Rated Vol.	D.F. ≤	Exception of D.F. ≤																																																		
		≥100V	≤3%	≤6%	1206≥0.47μF																																																	
				≤7.5%	0805>0.1μF,0603≥0.068μF,1206>1μF;1210≥2.2μF; TT series																																																	
				≤20%	0805>0.22μ;1210≥3.3μF																																																	
		50V	≤3%	≤6%	0201(50V);0603≥0.047μF;0805≥0.18μF;1206≥0.47μF																																																	
				≤10%	0201≥0.01μF;1210≥4.7μF																																																	
				≤20%	0402≥0.01μF;0603>0.1μF;0805≥1μF;1206≥2.2μF;1210≥10μF; TT series																																																	
		35V	≤5%	≤20%	0603≥1μF;0805≥2.2μF;1206≥2.2μF;1210≥10μF																																																	
		25V	≤5%	≤10%	0201≥0.01μF;0805≥1μF;1210≥10μF																																																	
				≤14%	0603≥0.33μ;1206≥4.7μF																																																	
				≤15%	0201≥0.1μF;0402≥0.10μF;0603≥0.47μ;0805≥2.2μF;1206≥6.8μF;1210≥22μF; TT series																																																	
				≤20%	0402≥0.47μF																																																	
		16V	≤5%	≤10%	0603≥0.15μF;0805≥0.68μF;1206≥2.2μ;1210≥4.7μF																																																	
		10V	≤7.5%	≤15%	0201≥0.012μF;0402≥0.33μF(0402/X7R≥0.22μF);0603≥0.33μF0805≥2.2μF;1206≥2.2μF;1210≥22μF																																																	
				≤20%	0201≥0.1μF;0402≥1μF; TT series; 01R5																																																	
		6.3V	≤15%	≤30%	0201≥0.1μF;0402≥1μF;0603≥10μF;0805≥4.7μF;1206≥47μF1210≥100μF; TT series																																																	
		4V	≤20%	---	---																																																	
		Y5V:	<table border="1"> <thead> <tr> <th>Rated Vol.</th> <th>D.F. ≤</th> <th colspan="2">Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td rowspan="2">≥50V</td> <td rowspan="2">≤7.5%</td> <td>≤10%</td> <td>0603≥0.1μF;0805≥0.47μF;1206≥4.7μF</td> </tr> <tr> <td>≤20%</td> <td>1210≥6.8μF</td> </tr> <tr> <td>35V</td> <td>≤10%</td> <td>---</td> <td>---</td> </tr> <tr> <td rowspan="2">25V</td> <td rowspan="2">≤7.5%</td> <td>≤10%</td> <td>0402≥0.047μF;0603≥0.1μF;0805≥0.33μF;1206≥1μF;1210≥4.7μF</td> </tr> <tr> <td>≤15%</td> <td>0402≥0.068μF;0603≥0.47μF;1206≥4.7μF;1210≥22μF</td> </tr> <tr> <td rowspan="2">16V (C≥1.0μF)</td> <td rowspan="2">≤10%</td> <td>≤12.5%</td> <td>0402≥0.068μF;0603≥0.68μF</td> </tr> <tr> <td>≤20%</td> <td>0402≥0.22μF</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>≤12.5%</td> <td>≤20%</td> <td>0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF;1812≥47μF</td> </tr> <tr> <td>10V</td> <td>≤20%</td> <td>≤30%</td> <td>0402≥0.47μF</td> </tr> <tr> <td>6.3V</td> <td>≤30%</td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated Vol.	D.F. ≤	Exception of D.F. ≤		≥50V	≤7.5%	≤10%	0603≥0.1μF;0805≥0.47μF;1206≥4.7μF	≤20%	1210≥6.8μF	35V	≤10%	---	---	25V	≤7.5%	≤10%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF;1206≥1μF;1210≥4.7μF	≤15%	0402≥0.068μF;0603≥0.47μF;1206≥4.7μF;1210≥22μF	16V (C≥1.0μF)	≤10%	≤12.5%	0402≥0.068μF;0603≥0.68μF	≤20%	0402≥0.22μF	16V (C≥1.0μF)	≤12.5%	≤20%	0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF;1812≥47μF	10V	≤20%	≤30%	0402≥0.47μF	6.3V	≤30%	---	---													
		Rated Vol.	D.F. ≤	Exception of D.F. ≤																																																		
		≥50V	≤7.5%	≤10%	0603≥0.1μF;0805≥0.47μF;1206≥4.7μF																																																	
				≤20%	1210≥6.8μF																																																	
		35V	≤10%	---	---																																																	
		25V	≤7.5%	≤10%	0402≥0.047μF;0603≥0.1μF;0805≥0.33μF;1206≥1μF;1210≥4.7μF																																																	
				≤15%	0402≥0.068μF;0603≥0.47μF;1206≥4.7μF;1210≥22μF																																																	
		16V (C≥1.0μF)	≤10%	≤12.5%	0402≥0.068μF;0603≥0.68μF																																																	
				≤20%	0402≥0.22μF																																																	
16V (C≥1.0μF)	≤12.5%	≤20%	0603≥2.2μF;0805≥3.3μF;1206≥10μF;1210≥22μF;1812≥47μF																																																			
10V	≤20%	≤30%	0402≥0.47μF																																																			
6.3V	≤30%	---	---																																																			
*I.R.: ≥10V, 500MΩ or 25 Ω-F whichever is smaller. Class II (X7R, X5R, Y5V)																																																						
<table border="1"> <thead> <tr> <th>Rated Voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: All X7R; 1210≥3.3μF</td> <td rowspan="7">1GΩ or RxC ≥ 10 Ω-F whichever is smaller</td> </tr> <tr> <td>50V: 0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF</td> </tr> <tr> <td>35V: 0603≥1μF;0805≥2.2μF;1206≥2.2μF;1210≥10F</td> </tr> <tr> <td>25V: 0201≥0.1μF;0402≥0.22μF;0603≥2.2μF; 0805≥2.2μF;1206≥10μF;1210≥10μF</td> </tr> <tr> <td>16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF; 0805≥2.2μF1206≥10μF;1210≥47μF</td> </tr> <tr> <td>10V:1201≥47nF;0402≥0.47μF;0603≥0.47μF; 0805≥2.2μF;1206≥4.7μF;1210≥47μF</td> </tr> <tr> <td>6.3V; 4V; TT series; Size≥1812</td> </tr> </tbody> </table>		Rated Voltage	Insulation Resistance	100V: All X7R; 1210≥3.3μF	1GΩ or RxC ≥ 10 Ω-F whichever is smaller	50V: 0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF	35V: 0603≥1μF;0805≥2.2μF;1206≥2.2μF;1210≥10F	25V: 0201≥0.1μF;0402≥0.22μF;0603≥2.2μF; 0805≥2.2μF;1206≥10μF;1210≥10μF	16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF; 0805≥2.2μF1206≥10μF;1210≥47μF	10V:1201≥47nF;0402≥0.47μF;0603≥0.47μF; 0805≥2.2μF;1206≥4.7μF;1210≥47μF	6.3V; 4V; TT series; Size≥1812																																											
Rated Voltage	Insulation Resistance																																																					
100V: All X7R; 1210≥3.3μF	1GΩ or RxC ≥ 10 Ω-F whichever is smaller																																																					
50V: 0402>0.01μF;0603≥1μF;0805≥1μF;1206≥4.7μF;1210≥4.7μF																																																						
35V: 0603≥1μF;0805≥2.2μF;1206≥2.2μF;1210≥10F																																																						
25V: 0201≥0.1μF;0402≥0.22μF;0603≥2.2μF; 0805≥2.2μF;1206≥10μF;1210≥10μF																																																						
16V:0201≥0.1μF;0402≥0.22μF;0603≥1μF; 0805≥2.2μF1206≥10μF;1210≥47μF																																																						
10V:1201≥47nF;0402≥0.47μF;0603≥0.47μF; 0805≥2.2μF;1206≥4.7μF;1210≥47μF																																																						
6.3V; 4V; TT series; Size≥1812																																																						

Reliability Test Conditions and Requirements Continued:

Item	Test Condition				Requirements			
High Temperature Load (Endurance)	*Test temp: NP0, X7R: 125±3°C X5R, Y5V: 85±3°C *To apply voltage: (1) ≤6.3V, C≥10µF or TT series:150% of rated vol. (2) 10V≤Ur<500V: 200% of rated voltage. (3) 500V: 150% of rated voltage. (4) Ur≥630V: 120% of rated voltage. (5) 100% of rated voltage for below range.				*No remarkable damage. Cap change: NP0: ±3.0% or ±0.3pF whichever is larger X7R, X5R: ≥10V**, within ±12.5%; ≤6.3V within ±25%; TT series & C≥1µF, within ±25% **10V: 0603≥4.7µF; 0402≥1µF; 0201≥0.1µF, within ±25% Y5V: ≥10V, within ±30%; ≤6.3V, within +30/-40% Q/D.F. value: NP0: More than 30pF, Q≥350 10pF≤C<30pF, Q≥275+2.5C Less than 10pf, Q≥200+10C X7R, X5R			
	Size	Dielectric	Rated Voltage	Capacitance Range	Rated Vol.	D.F. ≤	Exception of D.F. ≤	
0201	X5R/X7R	≤10V	C≥0.1µF	≥100V	≤3%	≤6%	1206≥0.47µF	
		≥16V	C>0.1µF			≤7.5%	0805>0.1µF;0603≥0.068µF; 1206>1µF;1210≥2.2µF; TT series	
0402	X5R/X7R/Y5V	6.3V, 10V, 16V, 25V	C≥1.0µF	50V	≤3%	≤20%	0805>0.22µ;1210≥3.3µF	
0603	X5R/X7R	4V	C≥2.2µF			≤6%	0201(50V);0603≥0.047µF;0805≥0.18µF;1206≥0.47µF	
		6.3V, 10V	C≥4.7µF	50V	≤3%	≤10%	0201≥0.01µF;1210≥4.7µF	
		25V, 35V	C≥1.0µF			≤20%	0402≥0.01µF;0603>0.1µF;0805≥1µF; 1206≥2.2µF;1210≥10µF; TT series	
0805	X5R/X7R	4V	C≥4.7µF	35V	≤5%	≤20%	0603≥1µF;0805≥2.2µF;1206≥2.2µF;1210≥10µF	
		6.3V	C≥2.2µF	25V	≤5%	≤10%	0201≥0.01µF;0805≥1µF;1210≥10µF	
1206	X5R/X7R	≥6.3V	C≥4.7µF			≤14%	0603≥0.33µ;1206≥4.7µF	
		3000V	C≥1.5pF	25V	≤5%	≤15%	0201≥0.1µF;0402≥0.10µF;0603≥0.47µ; 0805≥2.2µF;1206≥6.8µF;1210≥22µF; TT series	
1210	X5R/X7R	16V	C≥4.7µF			≤20%	0402≥0.47µF	
		100V	C≥3.3µF	16V	≤5%	≤10%	0603≥0.15µF;0805≥0.68µF;1206≥2.2µ;1210≥4.7µF	
TT15	X5R	6.3V	C>1.0µF			≤15%	0201≥0.01µF(0201/X7R≥0.022µF);0402≥0.033µF; 0603≥0.68µF;0805≥2.2;1206≥4.7µF;1210≥22µF; TT series	
TT18	Y5V	6.3V, 10V	C≥2.2µF	16V	≤5%	≤15%	0201≥0.1µF;0402≥1µF; TT series; 01R5	
		6.3V	C≥10µF			≤30%	0201≥0.1µF;0402≥1µF;0603≥10µF;0805≥4.7µF; 1206≥4.7µF 1210≥100µF; TT series	
TT21	Y5V	6.3V	C≥10µF	10V	≤7.5%	≤20%	0201≥0.012µF;0402≥0.33µF(0402/X7R≥0.22µF); 0603≥0.33µF0805≥2.2µF;1206≥2.2µF;1210≥22µF	
		≤10V	C≥10µF			≤20%	0201≥0.1µF;0402≥1µF; TT series; 01R5	
TT31	Y5V	6.3V	C≥2.2µF	6.3V	≤15%	≤30%	0201≥0.1µF;0402≥1µF;0603≥10µF;0805≥4.7µF; 1206≥4.7µF 1210≥100µF; TT series	
		6.3V	C≥2.2µF			---	---	
**1WV items must follow de-rating conditions (6)150% of rated voltage for below range.				6.3V	≤15%	≤30%	0201≥0.1µF;0402≥1µF;0603≥10µF;0805≥4.7µF; 1206≥4.7µF 1210≥100µF; TT series	
	Size	Dielectric	Rated Voltage	Capacitance Range	Rated Vol.	D.F. ≤	Exception of D.F. ≤	
	0201	X5R, X74	16V/25V	C≥0.1µF	4V	≤20%	---	
		X74	16V	C≥0.022µF	Y5V:	---	---	
	0402	X5R/X7R	50V	C≥0.1µF				
		Y5V	10~25V	C≥0.22µF	Rated Vol.	D.F. ≤	Exception of D.F. ≤	
		Y5V	16V	C≥0.47µF	≥50V	≤7.5%	≤10% 0603≥0.1µF;0805≥0.47µF;1206≥4.7µF	
	0603	X7R	50V	C>0.1µF	35V	≤10%	≤20%	1210≥6.8µF
		X5R/X74	10V, 16V, 50V	C≥1.0µF			---	---
		Y5V	16V	C≥2.2µF	25V	≤7.5%	≤10%	0402≥0.047µF;0603≥0.1µF; 0805≥0.33µF;1206≥1µF;1210≥4.7µF
	0805	X5R/X7R	10~50V	C≥4.7µF			≤15%	0402≥0.068µF;0603≥0.47µF; 1206≥4.7µF;1210≥22µF
		X5R/X7R	50V	C≥2.2µF	16V (C≥1.0µF)	≤10%	≤12.5%	0402≥0.068µF;0603≥0.68µF
		Y5V	100V	C≥0.47µF			≤20%	0402≥0.22µF
	1206	X5R/X7R	100V	C>1.0µF	16V (C≥1.0µF)	≤12.5%	≤20%	0603≥2.2µF;0805≥3.3µF;1206≥10µF; 1210≥22µF;1812≥47µF
	1210	X5R/X7R	50V~100v	C≥2.2µF			≤30%	0402≥0.47µF
	1825 2220 2225	X7R	100V~250V	C≥1.0µF	10V	≤20%	≤30%	0402≥0.47µF
					6.3V	≤30%	---	---
	*Test time: 1000+24/-0 hrs. *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. *Cap./DF(Q)/I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. ** De-rating conditions:				*I.R.:≥10V, 1GΩ or 50 Ω-F whichever is smaller Class II (X7R, X5R, Y5V)			
					Rated Voltage			Insulation Resistance
					100V: All X7R; 1210≥3.3µF			1GΩ or RxC ≥ 10 Ω-F whichever is smaller
					50V: 0402>0.01µF;0603≥1µF;0805≥1µF;1206≥4.7µF;1210≥4.7µF			
					35V: 0603≥1µF;0805≥2.2µF;1206≥2.2µF;1210≥10F			
					25V: 0201≥0.1µF;0402≥0.22µF;0603≥2.2µF;0805≥2.2µF;1206≥10µF;1210≥10µF			
					16V:0201≥0.1µF;0402≥0.22µF;0603≥1µF;0805≥2.2µF 1206≥10µF;1210≥47µF			
					10V:1201≥47nF;0402≥0.47µF;0603≥0.47µF; 0805≥2.2µF;1206≥4.7µF;1210≥47µF			
					6.3V; 4V; TT series; Size≥1812			

